



E-LTM 2408

Fiber Type: E-Glass
 Architecture: 0/90 Biaxial
 Dry Thickness: 0.040 in. / 1.02 mm
 Total Weight: 31.84 oz/sq.yd / 1080 g/sq.m

Roll Specifications			Fiber Architecture Data	
Roll Width: 50 in / 1270 mm	Roll Weight: 198 lb / 90 kg	Roll Length: 70 yd / 64 m	0 ° : 12.22 oz/sq.yd / 414 g/sq.m	
			45 ° : n/a	
			90 ° : 11.52 oz/sq.yd / 391 g/sq.m	
			-45 ° : n/a	
			Chopped Mat : 8.10 oz/sq.yd / 275 g/sq.m	

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

Laminated Properties

0 °

0 °

Laminate Weight				
	E-LTM 2408 Resin Infused		E-LTM 2408 Open Mold	
Fiber	0.22 lb/sq.ft	1.08 kg/sq.m	0.22 lb/sq.ft	1.08 kg/sq.m
Resin	0.11 lb/sq.ft	0.53 kg/sq.m	0.24 lb/sq.ft	1.19 kg/sq.m
Total	0.33 lb/sq.ft	1.61 kg/sq.m	0.47 lb/sq.ft	2.27 kg/sq.m

Physical Properties				
	E-LTM 2408 Resin Infused		E-LTM 2408 Open Mold	
Density	1.07 oz/cu.in	1.86 g/cc	0.93 oz/cu.in	1.60 g/cc
Fiber Content	67% by Wt.	49% by Vol.	48% by Wt.	30% by Vol.
Thickness	0.034 in	0.9 mm	0.056 in	1.4 mm

Laminate Moduli

	E-LTM 2408 Resin Infused		E-LTM 2408 Open Mold	
	Ex	2.91 MSI	20.06 GPa	1.95 MSI
Ey	2.85 MSI	19.67 GPa	1.91 MSI	13.20 GPa
Gxy	0.65 MSI	4.51 GPa	0.45 MSI	3.09 GPa
Ex,flex.	2.76 MSI	19.06 GPa	1.85 MSI	12.78 GPa
Ey,flex.	2.71 MSI	18.68 GPa	1.82 MSI	12.54 GPa

Ultimate Stress

	E-LTM 2408 Resin Infused		E-LTM 2408 Open Mold	
	Long. Ten.	42.8 KSI	295.0 MPa	28.7 KSI
Long. Comp.	53.0 KSI	365.8 MPa	35.6 KSI	245.4 MPa
Trans. Ten.	41.9 KSI	289.2 MPa	28.1 KSI	194.1 MPa
Trans. Comp.	57.0 KSI	393.3 MPa	38.3 KSI	263.9 MPa
In-Plane Shear	14.9 KSI	102.9 MPa	10.2 KSI	70.5 MPa
Long. Flex.	55.3 KSI	381.1 MPa	37.1 KSI	255.7 MPa
Trans. Flex.	57.4 KSI	395.7 MPa	38.5 KSI	265.5 MPa

In-Plane Stiffness, "EA"

	E-LTM 2408 Resin Infused		E-LTM 2408 Open Mold	
	(EA)x	99,096 lb/in	17,353 N/mm	108,980 lb/in
(EA)y	97,164 lb/in	17,015 N/mm	106,877 lb/in	18,716 N/mm
(GA)xy	22,300 lb/in	3,905 N/mm	25,034 lb/in	4,384 N/mm

Ultimate In-Plane Load

	E-LTM 2408 Resin Infused		E-LTM 2408 Open Mold	
	Long. Ten.	1,457 lb/in	255 N/mm	1,603 lb/in
Long. Comp.	1,807 lb/in	316 N/mm	1,987 lb/in	348 N/mm
Trans. Ten.	1,429 lb/in	250 N/mm	1,572 lb/in	275 N/mm
Trans. Comp.	1,943 lb/in	340 N/mm	2,138 lb/in	374 N/mm
In-Plane Shear	508 lb/in	89 N/mm	571 lb/in	100 N/mm

Notes:

- 1: Resin infused laminate made with a poly / vinyl ester resin blend.
- 2: Open mold laminate made with poly / vinyl ester resin blend.
- 3: All standard reinforcements should be infused with a flow aid or Vectorfusion® reinforcements.
- 4: All properties are given assuming a symmetric or quasisymmetric laminate schedule.



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

REV: 6/16/2015

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.