



E-TLX 2200

Fiber Type: E-Glass
 Architecture: 0/45/-45 Warp Triaxial
 Dry Thickness: 0.031 in. / 0.79 mm
 Total Weight: 23.55 oz/sq.yd / 799 g/sq.m

VECTORSPORTS™

Roll Specifications

Roll Width: 50 in / 1270 mm
 Roll Weight: 220 lb / 100 kg
 Roll Length: 106 yd / 97 m

Fiber Architecture Data

0 ° : 12.80 oz/sq.yd / 434 g/sq.m
 45 ° : 5.38 oz/sq.yd / 182 g/sq.m
 90 ° : n/a
 -45 ° : 5.38 oz/sq.yd / 182 g/sq.m
 Chopped Mat : n/a

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

Laminated Properties

0 °

0 °

Laminate Weight

(lb/sq.ft)	E-TLX 2200 Resin Infused	E-TLX 2200 Open Mold
Fiber	0.16	0.16
Resin	0.07	0.13
Total	0.23	0.30

Physical Properties

	E-TLX 2200 Resin Infused	E-TLX 2200 Open Mold
Density (g/cc)	1.90	1.69
Fiber Content (% by Wt.)	70%	55%
Thickness (in)	0.024	0.034

Laminate Modulii		
(MSI)	E-TLX 2200 Resin Infused	E-TLX 2200 Open Mold
Ex	4.18	3.03
Ey	2.12	1.51
Gxy	1.20	0.86
Ex,flex.	3.98	2.88
Ey,flex.	2.01	1.44

Ultimate Stress		
(KSI)	E-TLX 2200 Resin Infused	E-TLX 2200 Open Mold
Long. Ten.	79	57
Long. Comp.	79	57
Trans. Ten.	21	15
Trans. Comp.	21	15
In-Plane Shear	23	16
Long. Flex.	95	68
Trans. Flex.	20	14

In-Plane Stiffness, "EA"		
10 ³ lb/in	E-TLX 2200 Resin Infused	E-TLX 2200 Open Mold
(EA)x	99	102
(EA)y	50	51
(GA)xy	28	29

Ultimate In-Plane Load		
lb/in	E-TLX 2200 Resin Infused	E-TLX 2200 Open Mold
Long. Ten.	1,870	1,940
Long. Comp.	1,870	1,940
Trans. Ten.	500	511
Trans. Comp.	500	511
In-Plane Shear	538	549

Notes:

- 1: Resin infused laminate made with a poly / vinyl ester resin blend.
- 2: Open mold laminate made with poly / vinyl ester resin blend.
- 3: All standard reinforcements should be infused with a flow aid or Vectorfusion® reinforcements.



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

REV: 5/3/2011

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.